

COMPOSITES

Datasheet Sorlic® LRC



Lantor Sorlic® LRC

- The cost effective solution for closed mould processes
- Is used as core material and infusion medium
- Is a pressure stable polyester nonwoven and compatible with all regular types of resins, including Polyester, Vinylester, Phenolic and Epoxy
- Is suitable for closed mould processes, including Infusion, RTM Light, RTM Heavy

Applications Lantor Sorlic® LRC

- Marine: hulls, decks, and structures of boats and yachts
- Transportation: parts and panels of cars, trailers, trucks and RV's
- Mass transit: interior and exterior of trains, light rail and buses
- Leisure: kayaks, surfboards, pools and tubs
- Industrial: cladding panels, fans, containers and tanks
- Wind Energy: nacelle covers and spinners
- Infra structure: bridge panels

The information contained in this document has been compiled in good faith by Lantor BV, but nevertheless no representation or warranty is given as to the accuracy or completeness of the (technical) information provided herein. Lantor BV can not be held liable of any damages arising from any (printing) errors or omissions in this information. Lantor BV reserves the right to make changes with respect to the information provide at any time without further notice.

Dimensional data

Properties		LRC 1.5	LRC 2	LRC 3
Thickness	mm	1,5	2,0	3,0
Roll lenght	m	70	60	40
Roll width	m	1,27	1,27	1,27
Thickness loss at 0,8 bar	%	<15	<15	<15
Max processing temp.	°C	170	170	170
Resin uptake	kg/m ²	0,6	0,8	1,0
Dry weight	g/m ²	115	155	235
Density impregnated	kg/m ³	470	470	450

Typical mechanical properties of Lantor Sorlic® LRC* impregnated with unsaturated polyester resin

Mechanical properties	unit	value	test method
Flexural strenght	MPa	11	ASTM D790
Flexural modules	MPa	1015	ASTM D790
Tensile strenght across layers	MPa	3,5	ASTM C297
Compression strenght: 10% strain	MPa	4,5	ISO 844
Shear strenght	MPa	3	ASTM C273-61
Shear modules	MPa	26	ASTM C273-61
*Sorlic® LRC 2			

Information

PO box 45 - 3900 AA
Verlaat 22 - 3901 RG
Veenendaal
The Netherlands
T +31(0) 318 537 111
composites@lantor.com

enabling performance
www.lantor.com