

Technical Datasheet - METYX Composite Reinforcements

PRODUCT CODE	5200.002.172
PRODUCT NAME	X300E05C-45/45 BIAxIAL E GLASS FABRIC-127CM
PRODUCT DESCRIPTION	
CUSTOMER CODE	
CUSTOMER ID	

REINFORCEMENT CONSTRUCTION			
LAYER	FIBER TYPE	AREA WEIGHT	
1	+45°	E-GLASS 200 TEX	155 g/m ²
2	0°	E-GASS 68 TEX	1 g/m ²
3	-45°	E-GLASS 200 TEX	155 g/m ²
4	Stitch yarn	Polyester 7,6 TEX	5 g/m ²
5			
6			
7			

* Checked via own test based on ISO 3374.

TOTAL* 316 gr/m² (± %3)

OTHER PROPERTIES		ROLL INFO	
Stitch Gauge	5 stitches/inch	Roll Width	127 cm
Stitch Type	pillar	Roll Weight	66 kg
Stitch Length	3 mm	Roll Length	170 m
Pilot Yarn / Position	Blue-Yellow	Core Diameter	76 mm

Resin Compatibility	Loss on Ignition	Moisture Content
Polyester, Vinylester, Epoxy resins	Max.%0,70 by weight (ISO 1887)	Max.%0,20 by weight (ISO 3344)

Packaging	All rolls are wrapped with polyethylene bags; placed in pallet boxes or in single cardboard boxes or in pyramid style on pallets.
Labelling	Each roll is labelled on the inner side of the core, on the bag or on the cardboard boxes including a unique reference number for its traceability.
Storage	Store at %40-70 relative humidity and 18-30 °C temperature range. Recommended to be brought to working area 24 hrs prior to use.

Certification	DNV	Lloyd's Register
Metyx products are produced by Telateks A.S. company who is run by ISO 9001:2008 QA System.	TYPE Approved	-

Address:
Orhanli Beldesi 34956
Tuzla Istanbul – TURKIYE



Phone : +90-216-394-32-60
Fax : +90-216-394-32-58
Web : www.metyx.com